

Milling effects on magnetic properties of melt spun Fe-Nb-B alloy

J. J. Ipus, J. S. Blázquez, V. Franco, M. Stoica, and A. Conde

Citation: *Journal of Applied Physics* **115**, 17B518 (2014); doi: 10.1063/1.4866700

View online: <http://dx.doi.org/10.1063/1.4866700>

View Table of Contents: <http://scitation.aip.org/content/aip/journal/jap/115/17?ver=pdfcov>

Published by the [AIP Publishing](#)

Articles you may be interested in

[Analysis of heating effects \(magnetic hyperthermia\) in FeCrSiBCuNb amorphous and nanocrystalline wires](#)

J. Appl. Phys. **111**, 07A314 (2012); 10.1063/1.3672850

[Magnetocaloric response of Fe 75 Nb 10 B 15 powders partially amorphized by ball milling](#)

J. Appl. Phys. **105**, 123922 (2009); 10.1063/1.3155982

[Effect of Co substitution on the crystallization behavior and magnetic properties of melt-spun \(Pr,Tb \)₂ \(Fe,Nb,Zr \)₁₄ B /α- Fe nanocomposites](#)

J. Appl. Phys. **93**, 7978 (2003); 10.1063/1.1558273

[Dependence of the magnetic and magnetoelastic properties of \(TbFe₂ \)_{1-x} B_x melt-spun alloys on x](#)

J. Appl. Phys. **85**, 4500 (1999); 10.1063/1.370388

[Magnetic properties of Nd₈ Fe₇₇ Co₅ B₆ CuNb₃ melt-spun ribbons](#)

J. Appl. Phys. **83**, 6628 (1998); 10.1063/1.367928



Powerful, Multi-functional UV-Vis-NIR and FTIR Spectrophotometers

Providing the utmost in sensitivity, accuracy and resolution for applications in materials characterization and nano research

- Photovoltaics
- Polymers
- Thin films
- Paints
- Ceramics
- DNA film structures
- Coatings
- Packaging materials

[Click here to learn more](#)



Milling effects on magnetic properties of melt spun Fe-Nb-B alloy

J. J. Ipus,^{1,a)} J. S. Blázquez,¹ V. Franco,¹ M. Stoica,² and A. Conde¹

¹*Departamento de Física de la Materia Condensada, ICMSE-CSIC, Universidad de Sevilla, P.O. Box 1065, 41080 Sevilla, Spain*

²*IFW Dresden, Institute for Complex Materials, Helmholtzstr. 20, D-01069 Dresden, Germany*

(Presented 7 November 2013; received 20 September 2013; accepted 22 November 2013; published online 25 February 2014)

Fe₇₅Nb₁₀B₁₅ amorphous ribbons were grinded via ball milling to produce powder samples preserving the amorphous microstructure. A continuous increase of the Curie temperature with the milling time is observed as well as an enhancement of spontaneous magnetization, average hyperfine field, and magnetocaloric effect. This enhancement in the magnetic character of the samples as milling progresses is ascribed to an increase of the Fe-Fe distance. However, the peak entropy change reduces after grinding the ribbon sample. This effect could be related to a broader distribution of Curie temperatures in powdered samples. © 2014 AIP Publishing LLC.

[<http://dx.doi.org/10.1063/1.4866700>]

INTRODUCTION

Magnetocaloric effect at room temperature (RT) has deserved an increased attention of the research community in the last years¹ as the RT magnetic refrigeration is a promising technology, more energetically efficient compared to other types of RT conventional ones. Moreover, this new technology reduces the environmental impact avoiding the use of ozone depleting and global warming substances.

Fe-based amorphous alloys have been proposed to reduce material costs with respect to rare earth based compounds. Moreover, the second order phase transition present in these materials and their soft magnetic character yield negligible thermal and magnetic hysteresis losses. Although the research on magnetocaloric materials for RT applications has risen since the 90's, especially after the discovery of Gd₅Ge₂Si₂ compound,² the study of powder materials was delayed till the first decade of present century.^{3,4}

In order to produce powder samples, ball milling is a suitable technique that allows us to prepare a large amount of material. The microstructural evolution of the starting samples depends on several factors, such as the energy supplied to the powder during milling. There is a wide variety of transformations that can be induced by ball milling as amorphization, formation of metastable phases (solid solutions, quasicrystals), recrystallization of an amorphous phase, etc.⁵ When the starting system is heterogeneous, homogenization of the powder via mechanical alloying is achieved.

Although B is usually present in soft magnetic amorphous compositions, its atomic dissolution in the matrix via mechanical alloying is not completely successful when pure B phases are present in the starting mixture.⁶ Even the presence of impurities in FeB intermetallics leads to remaining B inclusions, which yield a lower B content in the amorphous phase than the nominal value and thus affecting several properties as crystallization and magnetic ones.⁶

In this work, amorphous Fe₇₅Nb₁₀B₁₅ melt spun ribbons were ball milled in order to study the evolution of the magnetocaloric response of the resulting powder samples as a function of the milling time while the initial amorphous structure is preserved during the process.

EXPERIMENTAL

Fe₇₅Nb₁₀B₁₅ amorphous alloy ribbon was produced by melt-spinning technique starting from high purity precursors which were arc-melted in Ar atmosphere. 15 g of ribbon was cut in pieces and introduced into the vials with a ball to powder ratio 10:1. Ball milling was performed in a planetary mill RETSCH PM400 using a rotational speed of 350 rpm. After some selected milling times, powder samples were taken out from the vials to characterize their microstructural evolution and magnetic properties.

Amorphous structure of the melt spun sample was checked by X-ray diffraction (XRD) using Cu-K α radiation in a Bruker D8I diffractometer. Local Fe environments were analyzed by Mossbauer spectrometry at room temperature in transmission geometry using a ⁵⁷Co(Rh) source. The values of the hyperfine parameters were obtained by fitting with the different spectra imposing a hyperfine field distribution from 0 to 33 T in NORMOS program.⁷ A figure with Mössbauer spectra and hyperfine field distributions is available as supplementary material.⁸ Isothermal magnetization curves were measured using a Lakeshore 7407 vibrating sample magnetometer (VSM) with a maximum applied field of $H = 1.5$ T, field steps of 250 Oe and in the temperature range from 77 K to 573 K with increments of 10 K. Spontaneous magnetization, σ_0 , was obtained from the extrapolation of high field magnetization curves, $M(H)$, to zero field. Curie temperature, T_C , was calculated as the inflexion point of $\sigma_0(T)$ curves. Magnetic entropy change, ΔS_M due to the application of a magnetic field has been calculated by processing the temperature and field dependent magnetization curves using a numerical approach to the equation

^{a)}Author to whom correspondence should be addressed. Electronic mail: jhonipus@us.es.

$$\Delta S_M = \int_0^{H_{MAX}} \left(\frac{dM}{dT} \right)_H dH. \quad (1)$$

The partial derivatives are replaced by finite differences and the integration is performed numerically from zero field to the maximum value H_{MAX} .

RESULTS AND DISCUSSION

Microstructural evolution with milling process is shown in the XRD patterns of Figure 1. It can be seen that the amorphous structure of the initial melt spun sample is preserved throughout the explored milling time. In order to extract some information from the patterns, these were fitted using a Gaussian profile for the amorphous phase and imposing a Lorentzian profile to simulate possible nanocrystals in the 2θ range where the (110) bcc-Fe diffraction line should appear. No important crystalline contribution was found in the patterns (estimated crystalline fraction $<2\%$, below the precision of the method). The position of the halo shifts to lower 2θ values as milling progresses, which indicates an expansion of the average Fe-Fe distance. The inset of Figure 1 shows the evolution of the metal-metal distances estimated as⁹

$$\delta_{M-M} = \frac{5\lambda}{8 \sin(\theta)}, \quad (2)$$




FIG. 1. XRD patterns of the as-cast ribbon and powder samples after different milling times. Inset shows the evolution of the metal-metal distance as a function of milling time.

where λ is the wavelength of the used radiation. The width of the fitted Fe-Fe distance distribution is ~ 0.50 nm, independently of the milling time.

Figure 2 shows the milling time dependence of room temperature values of the spontaneous magnetization and the average hyperfine magnetic field. Both parameters are well correlated and increase monotonically with the milling time. This magnetic enhancement is also reflected in the evolution of T_C . At this temperature, these samples exhibit a second order phase transition, which implies a peak in the magnetic entropy change, ΔS_M^{pk} , as shown in Figure 3. This peak value reduces after 0.5 h milling, although further milling leads to a monotonous increase of ΔS_M^{pk} , reaching similar values to that of the ribbon sample after 20 h milling (see inset of Fig. 3). The initial reduction of ΔS_M^{pk} after powdering the sample is not reflected in the spontaneous magnetization, which even increases from 44.8 to 51.4 emu/g. However, a clear broadening of the magnetocaloric peak and a smaller slope in the $\sigma_0(T)$ curve of sample milled 0.5 h with respect to the ribbon one, should indicate a broader distribution of Curie temperatures in powder samples. The peak temperature, T^{pk} , which is almost coincident with T_C , at moderately small fields for these materials,¹⁰ also increases with milling from 325 K, for melt spun ribbon, to 395 K after 40 h milling (see inset of Fig. 3). It is worth mentioning that the demagnetizing factor $N = 1/3$ for approximately spherical powder particles should slightly modify the results shown in Figure 3, but those changes would not affect the conclusions of this work.

In order to evidence the relationship between the magnetic properties and the Fe-Fe distance, Figure 4 shows T_C versus the average metal-metal distance calculated from XRD data. A linear correlation is found indicating that as the Fe-Fe distance increases, the ferromagnetic character of the powder is enhanced. This result is in agreement with literature data on pressure effect on the magnetism on Fe-based alloys without phase transformation. In those cases, the contraction of the structure due to the increase of pressure reduces both magnetization and T_C .^{11,12} Moreover, considering the Slater-Pauling curve for Fe-Co, the magnetic moment of Fe atoms increases as the separation between atoms




FIG. 2. Milling time dependence of the room temperature spontaneous magnetization and average hyperfine magnetic field. Error bars are smaller than the symbol sizes.




FIG. 3. Magnetic entropy change for as-cast ribbon and powder samples milled for different times. Inset shows the milling time dependence of the peak entropy change and peak temperature.




FIG. 4. Curie temperature as a function of the average metal-metal distance.

increases.¹³ However, it should be noted that a distribution in the Fe-Fe distance intrinsic in the amorphous structures would produce a distribution of the exchange coupling constant, as studied by Gallagher *et al.*¹⁴ This also originates a broadening of the magnetocaloric peak.¹⁵ Nevertheless, even if this distribution should have an influence, as in our case the width of the Fe-Fe distance distribution remains constant for the different samples, the differences observed in their magnetocaloric response should not be ascribed to this effect.

CONCLUSIONS

Amorphous Fe₇₅Nb₁₀B₁₅ ribbons were powdered via ball milling and the evolution of the microstructure and magnetic properties as a function of milling time were studied. From this study, some conclusions can be derived:

- The amorphous structure of the initial ribbon was retained during milling but an increase of the distance between Fe atoms was observed as milling progresses.
- Some changes have been observed in the magnetic properties ascribed to an increase in the Fe-Fe distance as milling time increases: the Curie temperature of the powder samples continuously increases, the spontaneous magnetization and the average hyperfine magnetic field also increase, as well as the magnetic entropy change of the powder samples.
- The magnetic entropy change observed for short milling times is lower than those observed for the ribbon sample even though spontaneous magnetization increases after short milling. This effect is ascribed to a broader distribution of Curie temperatures in the powder samples with respect to that of the ribbon sample.

ACKNOWLEDGMENTS

This work was supported by the Spanish Ministry of Science and Innovation (MICINN) and EU FEDER (project MAT2010-20537), the PAI of the Regional Government of Andalucía (RGA) (project P10-FQM-6462), and the United States Office of Naval Research (Project N00014-11-1-0311). J.J.I. acknowledges a research fellowship from RGA.

- ¹V. Franco, J. S. Blázquez, B. D. Ingale, and A. Conde, *Annu. Rev. Mater. Res.* **42**, 305–342 (2012).
- ²V. K. Pecharsky and K. A. Gschneidner, Jr., *Phys. Rev. Lett.* **78**, 4494–4497 (1997).
- ³F. Q. Zhao, W. Dagula, O. Tegus, T. J. Gortenmulder, E. Bruck, and K. H. J. Buschow, *IEEE Trans. Mag.* **41**, 3754–3756 (2005).
- ⁴Y. X. Zhang, Z. G. Liu, H. H. Zhang, and X. N. Xu, *Mater. Lett.* **45**, 91–94 (2000).
- ⁵C. Suryanarayana, *Prog. Mater. Sci.* **46**, 1–184 (2001).
- ⁶J. J. Ipus, J. S. Blázquez, C. F. Conde, V. Franco, J. M. Borrego, S. Lozano-Perez, and A. Conde, *Intermetallics* **49**, 98–105 (2014).
- ⁷R. A. Brand, J. Lauer, and D. M. Herlach, *J. Phys. F: Met. Phys.* **13**, 675–683 (1983).
- ⁸See supplementary material at <http://dx.doi.org/10.1063/1.4866700> for Mössbauer spectra and hyperfine field distributions for as-milled samples.
- ⁹T. Egami, *Rapidly Solidified Alloys: Processes, Structures, Properties, Applications*, edited by H. H. Liebermann (Marcel Dekker, Inc., New York, 1993), p. 232.
- ¹⁰V. Franco, A. Conde, M. D. Kuzmin, and J. M. Romero-Enrique, *J. Appl. Phys.* **105**, 07A917 (2009).
- ¹¹I. V. Medvedeva, Y. S. Bersenev, A. A. Ganin, K. Bärner, J. W. Schünemann, and K. Heinemann, *J. Magn. Magn. Mater.* **124**, 293–297 (1993).
- ¹²A. Martínez, J. J. Romero, F. Bartolomé, L. M. García, F. Baudelet, A. Hernando, and P. Crespo, *Appl. Phys. Lett.* **101**, 022412 (2012).
- ¹³R. M. Bozorth, *Ferromagnetism* (Van Nostrand, Princeton, 1968).
- ¹⁴K. A. Gallagher, M. A. Willard, W. N. Zabenkin, D. E. Laughlin, and M. E. McHenry, *J. Appl. Phys.* **85**, 5130–5132 (1999).
- ¹⁵N. J. Jones, H. Ucar, J. J. Ipus, M. E. McHenry, and D. E. Laughlin, *J. Appl. Phys.* **111**, 07A334 (2012).