

KINETIC STUDIES IN SOLID STATE REACTIONS BY SMART TEMPERATURE METHODS AND ADVANCED ANALYSIS PROCEDURES

Luis A. Pérez-Maqueda, José M. Criado, Pedro E. Sánchez-Jiménez and Antonio Perejón*

Instituto de Ciencia de Materiales de Sevilla, Universidad de Sevilla- C.S.I.C, c/Américo Vespucio 49, 41092 Sevilla (Spain).

ABSTRACT

A comparative study of both conventional rising temperature and smart temperature control methods, like Constant Rate Thermal Analysis (CRTA), is carried out after analysing a set of solid state reactions using both methods. It is shown that CRTA avoids the influence of heat and mass transfer phenomena for a wide range of sample sizes leading to reliable kinetic parameters. On the other hand, conventional rising temperature methods yield α - T plots dependent on experimental conditions, even when using samples sizes smaller than 2 mg. Moreover, it is shown that the discrimination of overlapping processes is dramatically improved by using smart temperature control methods instead of conventional heating procedures. An advanced method for performing the kinetic analysis of complex processes from a single CRTA experiment is proposed.

INTRODUCTION

Smart temperature methods for studying chemical reactions imply controlling the temperature in such a way that the reaction itself follows a trend previously designed by the user. The most widely used smart temperature control method is the Constant (or Controlled) Rate Thermal Analysis (CRTA), independently developed by Rouquerol [1, 2] and the Paulik brothers [3]. This method involves controlling the temperature in such a way that the reaction rate is maintained constant all over the process. CRTA has been used by several authors for the synthesis of different materials, such as catalysts and sorbents with controlled porosity [4-24], structural ceramics [25-28] or electroceramics [29-32] and for binder burnout [33-35]. Besides it has many applications in analytical chemistry [36-39]. CRTA has been also extensively applied to the kinetic analysis of solid state reactions [40-61], after Criado et al. [62, 63] showed

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
the advantages of this method as compared to conventional rising temperature ones for discriminating among the different kinetic models. It was demonstrated that, while conventional rising temperature $\alpha-T(t)$ plots always present a sigmoidal shape independently of the reaction mechanism, the shape of the CRTA curves is strongly dependent on the reaction mechanism. Thus, the curves corresponding to “n order” models are convex with regards to the T axis, while those following diffusion kinetic equations present an inflection point and, finally, curves obeying an Avrami-Erofeev kinetic model show a minimum in temperature for certain value of α . Thus, CRTA experiments corresponding to reactions following this latter mechanism start with a rise in temperature until reaching the preset value of the reaction rate. This step is immediately followed by a temperature fall until reaching a determined value of the reacted fraction that depends on the n coefficient of the Avrami-Erofeev equation; then the temperature rises again until the reaction is over.

25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
On the other hand, it has been claimed [61, 64] that CRTA has higher resolution power than conventional non-isothermal methods for discriminating mutually independent overlapping reactions. This behavior can be understood as a consequence of the high level of control provided by CRTA, i.e. the reaction rate is measured with a great accuracy (since it is constant), the uncertainty about the sample temperature is reduced by imposing a low reaction rate that minimize the temperature gradients while the surrounding atmosphere is also well controlled because of the reduction of the pressure gradients. In other words, CRTA provides almost automatically the experimental conditions required for meaningful and reliable kinetic experiments. Three different examples are presented, which illustrate the ability of CRTA for avoiding the influence of heat and mass transfer phenomena leading to reliable kinetic data and for discriminating overlapping processes in complex reactions (blended materials).

52 53 54 **EXPERIMENTAL PART**

55
56
57
58
59
60
61
62
63
64
65
The following materials were used: PbCO_3 supplied by Merck, PVC fine powder (with average $M_n = 47000$ and average $M_w = 80.000$) supplied by Aldrich and a sample of PVC

1 blended with a 33% of DINCH (1,2cyclohexane dicarbocyclic acid, diisononyl ester) as
2 plasticizer.

3
4 For thermal analysis experiments, a homemade system that allows working under a
5 vacuum better than $2 \cdot 10^{-6}$ mbar or under a controlled flow of any inert or reactive
6 permanent gas and in the temperature range from room temperature to 1250 K has
7 been attached to a CI Electronic electrobalance.
8

9
10 The thermal decomposition of PbCO_3 was studied under both conventional linear
11 heating rate and CRTA conditions in vacuum. Samples were outgassed at room
12 temperature until reaching the best vacuum available ($4 \cdot 10^{-5}$ mbar). For linear heating
13 rate experiments sample sizes smaller than 5 mg were used. CRTA experiments were
14 carried out using the Rouquerol approach [65]. It consists on monitoring the furnace
15 temperature in such a way that the pumping rate and the residual pressure in the
16 close vicinity of the sample is maintained constant all over the process. The CRTA
17 diagrams were recorded using a constant CO_2 residual pressure of $4 \cdot 10^{-5}$ mbar and a
18 constant decomposition rate of about $1.6 \cdot 10^{-3} \text{ min}^{-1}$. A starting sample size of 20 mg
19 was used. In addition, a cyclic CRTA experiment was performed using a sample size of
20 100 mg. In such case two decomposition rates were set at $1.6 \cdot 10^{-3} \text{ min}^{-1}$ and $1.9 \cdot 10^{-3}$
21 min^{-1} and they were maintained constant during alternative periods of 1 hour. These
22 conditions allow performing about 15 cycles during the decomposition of the PbCO_3 .
23 For PVC and PVC blend, experiments were performed under 100 ml min^{-1} nitrogen flow
24 using both linear heating rate and CRTA experiments. For the CRTA experiments, the
25 temperature was controlled in such a way that the mass change as a function of time
26 fits a predefined linear function. A detailed description of this temperature control
27 system can be found in a previous reference [66].
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47

48 **THEORETICAL PART**

49
50
51 The reaction rate of a solid state reaction can be represented by the following
52 equation:
53

$$54 \frac{d\alpha}{dt} = A \exp\left(-\frac{E}{RT}\right) f(\alpha) \quad (1),$$

55
56
57
58
59
60
61
62
63
64
65

1 where α is the reacted fraction, t is the time, $d\alpha/dt$ is the reaction rate, T is the
2 temperature, A is the preexponential factor of Arrhenius, E is the activation energy, R
3 is the gas constant and $f(\alpha)$ is a function representing the kinetic model.

4 Eq. (1) must be accomplished whatever would be the thermal pathway followed for
5 achieving a particular point of the triplet $(d\alpha/dt)$ - α - T . If the α - T (or t) plot is obtained at
6 a constant decomposition rate ($C = d\alpha/dt$), Eq. (1) can be rearranged, after taking
7 logarithms, in the form:
8
9

$$10 \quad -\ln f(\alpha) = \ln \frac{A}{C} - \frac{E}{RT} \quad (2).$$

11
12
13
14
15 The plot of the left hand side of Eq. (2) as a function of $1/T$ leads to a straight line,
16 where the slope leads to the activation energy and the intercept to the pre-
17 exponential factor of the Arrhenius expression of the process, provided that the
18 proper $f(\alpha)$ function is selected, except if the kinetic model is represented by the
19 function $f(\alpha) = (1-\alpha)^n$, i.e. R2, R3 and F1 models, frequently referred as “ n order”
20 reactions. In such a case, Eq. (2) becomes:
21
22
23
24

$$25 \quad -\ln(1 - \alpha) = \ln \frac{A}{nC} - \frac{E}{nRT} \quad (3)$$

26
27
28
29 E and n cannot be simultaneously determined from a single experiment unless one of
30 these two parameters is known from other source. The method of *Cyclic Reaction*
31 *Rate* also named *Rate Jump method* proposed by Rouquerol [67] would allow
32 overcoming this limitation. This method imposes periodical jumps between two pre-
33 set decomposition rates and compares the state of the sample immediately before the
34 rate jump, at which the reaction rate is C_1 and the temperature is T_1 , with the state
35 immediately after the jump, at which the reaction rate and the temperature have
36 moved to C_2 and T_2 , respectively. Taking into account that the two states of the sample
37 to be compared have practically the same reacted fraction, one gets
38
39
40
41
42
43

$$44 \quad E = \frac{RT_1T_2}{(T_2 - T_1)} \ln \frac{C_2}{C_1} \quad (4).$$

45
46
47
48 Equation (4) permits to obtain the activation energy of the process without any
49 assumption regarding the kinetic law obeyed by the reaction. The value of the
50 “reaction order” n can be determined from Eq. (3) once the activation energy has been
51 determined from Eq. (4).
52
53
54
55
56
57
58
59
60
61
62
63
64
65

RESULTS AND DISCUSSION

CRTA and control of the heat and mass transfer phenomena

The study of the thermal decomposition of lead carbonate illustrates the advantages of CRTA for minimizing the influence of mass and/or heat transfer phenomena on the forward reaction in order to get reliable kinetic information. The study of this reaction from rising temperature thermogravimetric experiments recorded under high vacuum has shown that it is not possible to obtain TG curves independent of the starting sample mass, not even for sample sizes smaller than 2 mg and heating rates as low as 0.5 K min^{-1} , as illustrated in Fig. 1. These results clearly demonstrate that it is not possible to derive reliable kinetic data of the thermal decomposition of this carbonate from conventional TG, even under high vacuum, which is expected to minimize the influence of the CO_2 self-generated in the thermal decomposition.

Figure 2 shows the α - T CRTA curve obtained at constant decomposition rate, i.e. $C = 1.6 \cdot 10^{-3} \text{ min}^{-1}$, for a starting sample size of 20 mg. The concave shape of the plot suggests that the thermal decomposition of PbCO_3 obeys an "n order" reaction and, therefore, as stated in the theoretical section, it is not possible to determine simultaneously the activation energy and the exponent n . However, the value of E/n can be obtained from the slope of the plot of the left hand side of Eq. (3) versus $1/T$ as indicated in the theoretical section, yielding a value of $E/n = 122 \text{ kJ mol}^{-1}$. An additional cyclic CRTA experiment has been carried out under the experimental conditions described in the experimental section, for calculating the activation energy. Fig. 3 shows a detail of a tooth taken from the cyclic CRTA curve. The activation energy determined from this cycle is $E = 121 \text{ kJ mol}^{-1}$, while very similar values were obtained for each of the 15 cycles recorded from $\alpha = 0.05$ up to $\alpha = 0.95$, leading to an average value of $E = 120 \pm 10 \text{ kJ mol}^{-1}$. The comparison of this E value with the E/n value, obtained for the CRTA curve in Fig. 2, shows that the thermal decomposition of PbCO_3 fits a F1 kinetic model, i.e. $n=1$. It is noteworthy to remark that the α - T points taken from the traces of the cyclic CRTA curve at which the decomposition rate is equal to $1.6 \cdot 10^{-3} \text{ min}^{-1}$ matches the CRTA of Fig. 2 recorded at the same constant decomposition rate, as shown in Fig. 2 with the superimposed points. This behavior clearly demonstrates that the α - T plots here obtained by the CRTA method are quite independent of the starting sample mass, unlike those obtained under rising temperature experiments, as it was previously shown in Fig. 1.

Advanced kinetics procedure for complex reactions

The kinetics of the thermal dehydrochlorination of polyvinyl chloride (PVC) was carried out in a previous paper [56]. In such work, it was concluded that the reaction takes place in two independent steps that were separated using an advanced kinetic analysis procedure, which involves the simultaneous analysis of a set of TG curves

1 obtained at different heating rates. It was shown [56] that the first step fits an Avrami-
 2 Erofeev kinetic model, followed by a second overlapping step that obeys a diffusion
 3 kinetic model. The microscopic observations support that the reaction follows an
 4 Avrami-Erofeev kinetic model (formation and growth of nuclei) and that part of the HCl
 5 formed in the dehydrochlorination reaction is trapped into bubbles and later released
 6 as the temperature increases. This latter process accounts for the second diffusion
 7 step.
 8
 9

10 The use of CRTA simplifies the kinetic analysis by improving the resolution of
 11 overlapping processes. This method provides a much better discrimination power of
 12 the solid state reaction kinetic models than conventional linear heating or isothermal
 13 experiments, because the shape of the CRTA α - T curve is dependent on the kinetic
 14 model followed by the process, unlike curves recorded under linear heating rate
 15 conditions, that always have a sigmoidal shape [61-63].
 16
 17

18 Figure 4 shows the α - T plot obtained at a constant decomposition rate, i.e. $C = 6.10^{-3}$
 19 min^{-1} , for the thermal dehydrochlorination of PVC. Two overlapping steps are clearly
 20 observed in this figure. At the initial part, temperature sharply rises, until reaching the
 21 preset value of the reaction rate. At this point temperature immediately drops, until
 22 reaching a certain conversion value, followed by a new temperature rise. Thus, the
 23 curve falls back on itself upon achieving the preset constant rate. This shape is
 24 characteristic of a nucleation and growth of nuclei mechanism [61-63]. The shape of
 25 the second part of the curve is more difficult to discriminate because of the
 26 overlapping, but it seems to have a sigmoidal shape characteristic of diffusion
 27 processes [61-63].
 28
 29

30 A complete kinetic analysis of this complex reaction requires deconvoluting the overall
 31 curve into its individual processes and determining their kinetic parameters, i.e.
 32 activation energies, preexponential factors and kinetic models. No solution is found if
 33 the deconvolution of the overlapping curves is attempted by assuming two parallel
 34 competitive reactions, in agreement with the conclusion of Sánchez-Jiménez et al.
 35 [56], where two independent reactions are considered. Thus, the deconvolution has
 36 been carried out by resolving the following system of differential equations:
 37
 38
 39
 40
 41
 42
 43
 44

$$45 \quad C = \frac{d\alpha}{dt} = l_1 A_1 \exp\left(-\frac{E_1}{RT}\right) f_1(\alpha_1) + l_2 A_2 \exp\left(-\frac{E_2}{RT}\right) f_2(\alpha_2) \quad (5)$$

$$46 \quad l_1 + l_2 = 1 \quad (6)$$

$$47 \quad l_1 \alpha_1 + l_2 \alpha_2 = \alpha \quad (7),$$

48 where the subscripts 1 and 2 correspond to the first and second process, respectively,
 49 l_1 and l_2 being the contribution fraction of each process. It has been shown in a
 50 previous paper [68] that the $f(\alpha)$ functions of all the different kinetic models proposed
 51 in literature can be represented by the following modified Sestak-Berggren equation,
 52
 53
 54
 55
 56
 57
 58
 59
 60
 61
 62
 63
 64
 65

1 i.e. $f(\alpha) = c \alpha^m(1-\alpha)^n$. This empirical approximation also accounts for deviations from
2 the ideal kinetic models due to inhomogeneities in shape and particle size distribution.
3 Thus, the modified Sestak-Berggren equation has been used for $f_1(\alpha_1)$ and $f_2(\alpha_2)$ in Eq.
4 (5).

5 All the kinetic parameters are determined by comparing the experimental curve with
6 the theoretical one obtained from Eqns. (5), (6) and (7) using iterative optimization.
7

8 Considering the CRTA shape analysis discussed before, the experimental curve was
9 fitted assuming Avrami-Erofeev and tridimensional diffusion mechanisms for the
10 beginning and the end of the reaction, respectively, while the resulting kinetic
11 parameters were used as starting values for the optimization process. The iterative
12 optimization procedure yielded the following kinetic parameters: $l_1 = 0,66$, $E_1 = 113$
13 kJ/mol, $c_1A_1 = 5,8 \cdot 10^{10} \text{ min}^{-1}$, $n_1 = 1,17$, $m_1 = 0,68$; $l_2 = 0,34$, $E_2 = 202$ kJ/mol, $c_2A_2 = 1,1 \cdot$
14 10^{17} min^{-1} , $n_2 = 1.37$ and $m_2 = -1.89$. These values are in very good agreement with
15 those previously reported [69] for the same sample from the simultaneous kinetic
16 analysis of a set of TG diagrams obtained under different heating rates. Moreover, the
17 theoretical curve constructed with these parameters matches quite well the
18 experimental curve, as shown in Fig. 4.
19

20 The values of n_1 and m_1 agree with the values expected for an A_2 Avrami-Erofeev
21 kinetic model, while the values obtained for n_2 and m_2 agree with the values expected
22 for a tridimensional diffusion controlled reactions as shown in previous references [56,
23 69]. In summary, the results here reported show that CRTA method considerably
24 simplifies the kinetic analysis of complex processes.
25

26 *Applications of the resolution power of CRTA methods in Analytical Chemistry*

27 Elastomers often contain an appreciable amount of oil as a plasticizer. Hammer [70]
28 has shown that in many cases, accurate determination of oil and polymer content is
29 difficult because oil vaporization and elastomer thermal decomposition overlap. CRTA
30 method is a powerful tool for overcoming this problem.
31

32 The higher resolution power of CRTA with regards to conventional rising temperature
33 methods is of great interest for increasing the efficiency of thermogravimetry as an
34 analytical tool. It has been shown in a recent paper [37] that CRTA allows to perform
35 compositional analysis of multicomponent polymeric materials by means of
36 thermogravimetric experiments. Fig. 5 shows the conventional linear heating rate and
37 CRTA curves obtained for PVC blended with DINCH plasticizer (1,2-cyclohexane
38 dicarbocyclic acid diisononyl ester). It can be observed that the CRTA curve leads to a
39 complete separation of both the evaporation of the plasticizer and the thermal
40 decomposition of the polymer. This is not achieved in the curve recorded under linear
41 heating rate conditions where both processes totally overlap. Besides, the shape of α - T
42 plot corresponding to the dehydrochlorination of PVC, as shown in Fig. 4, is observed in
43 the second step of the CRTA curve of Fig. 5, after the plasticizer is released. Thus, it can
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

be concluded that CRTA constitutes a powerful tool for determining the percentage of plasticizers contained in blended polymers, avoiding the use of chromatographic techniques that are rather cumbersome and time consuming [71, 72].

AKNOWLEDGEMENT

We thank Spanish Government (project CTQ 2011-27626) partially supported by FEDER funds for financial support. We are grateful to Prof. Juan López and Dr. José E. Crespo-Amorós for providing access to their lab to prepare the PVC blends.

REFERENCES

1. Ganteaume M, Rouquerol J. Kinetic study on thermal-decomposition by coupling calorimetry and thermal-analysis at constant decomposition rate. *J Therm Anal.* 1971;3(4):413-&.
2. Rouquerol J. Methode danalyse thermique sous faible pression et a vitesse de decomposition constante. *Bull Soc Chim Fr.* 1964 (1):31-&.
3. Paulik J, Paulik F. Quasi-isothermal thermogravimetry. *Anal Chim Acta.* 1971;56(2):328-&.
4. Ganteaume M, Rouquerol F, Rouquerol J. Comparative effect of 2 parameters (pressure and decomposition speed) on texture of divided oxides (gallium oxide and alumina) from thermal decomposition of corresponding hydroxides. *J Chim Phys Phys-Chim Biol.* 1968;65(4):587-&.
5. Rouquerol J, Rouquerol F, Ganteaume M. Thermal-decomposition of gibbsite under low-pressures .1. Formation of boehmitic phase. *J Catal.* 1975;36(1):99-110.
6. Rouquerol J, Rouquerol F, Ganteaume M. Thermal-decomposition of gibbsite under low-pressures .2. Formation of microporous alumina. *J Catal.* 1979;57(2):222-30.
7. Paulik F, Paulik J, Naumann R, Kohnke K, Petzold D. Mechanism and kinetics of the dehydration of hydrargillites .1. *Thermochim Acta.* 1983;64(1-2):1-14.
8. Dufau N, Luciani L, Rouquerol F, Llewellyn P. Use of sample controlled thermal analysis to liberate the micropores of aluminophosphate alpo4-11: Evidence of template evaporation. *J Mater Chem.* 2001;11(4):1300-4.
9. Sicard L, Llewellyn PL, Patarin J, Kolenda F. Investigation of the mechanism of the surfactant removal from a mesoporous alumina prepared in the presence of sodium dodecylsulfate. *Microporous Mesoporous Mater.* 2001 Jun;44:195-201.
10. Keene MTJ, Gougeon RDM, Denoyel R, Harris RK, Rouquerol J, Llewellyn PL. Calcination of the mcm-41 mesophase: Mechanism of surfactant thermal degradation and evolution of the porosity. *J Mater Chem.* 1999 Nov;9(11):2843-50.
11. Rouquerol F, Rouquerol J, Thevand G, Triaca M. Desorption of chemisorbed species - its study by controlled rate thermal-analysis. *Surf Sci.* 1985;162(1-3):239-44.
12. Torralvo MJ, Grillet Y, Rouquerol F, Rouquerol J. Application of crta to the study of microporosity by thermodesorption of preadsorbed water. *J Therm Anal.* 1994 Jun;41(6):1529-34.
13. Barnes PA, Parkes GMB. A new approach to catalyst preparation using rate controlled temperature programme techniques. Poncelet G, Martens J, Delmon B, Jacobs PA, Grange P, editors1995. 859-68 p.
14. Barnes PA, Parkes GMB, Brown DR, Charsley EL. Applications of new high resolution evolved gas analysis systems for the characterisation of catalysts using rate-controlled thermal analysis. *Thermochim Acta.* 1995;269:665-76.

15. Dawson EA, Parkes GMB, Barnes PA, Chinn MJ, Norman PR. A study of the activation of carbon using sample controlled thermal analysis. *J Therm Anal Calorim.* 1999;56(1):267-73.
16. Charsley EL, Rooney JJ, Hill JO, Parkes GMB, Barnes PA, Dawson EA. Development and applications of a preparative scale sample controlled thermogravimetric system. *J Therm Anal Calorim.* 2003;72(3):1091-.
17. Fesenko EA, Barnes PA, Parkes GMB, Dawson EA, Tiernan MJ. Catalyst characterisation and preparation using sample controlled thermal techniques - high resolution studies and the determination of the energetics of surface and bulk processes. *Top Catal.* 2002;19(3-4):283-301.
18. Dawson EA, Parkes GMB, Barnes PA, Chinn MJ. An investigation of the porosity of carbons prepared by constant rate activation in air. *Carbon.* 2003;41(3):571-8.
19. Chopra GS, Real C, Alcalá MD, Pérez-Maqueda LA, Subrt J, Criado JM. Factors influencing the texture and stability of maghemite obtained from the thermal decomposition of lepidocrocite. *Chem Mater.* 1999;11(4):1128-37.
20. Pérez-Maqueda LA, Criado JM, Real C, Subrt J, Bohacek J. The use of constant rate thermal analysis (CRTA) for controlling the texture of hematite obtained from the thermal decomposition of goethite. *J Mater Chem.* 1999;9(8):1839-46.
21. Pérez-Maqueda LA, Criado JM, Subrt J, Real C. Synthesis of acicular hematite catalysts with tailored porosity. *Catal Lett.* 1999;60(3):151-6.
22. Pérez-Maqueda LA, Sánchez-Jiménez PE, Criado JM. Sample controlled temperature (SCT): A new method for the synthesis and characterization of catalysts. *Current Topics in Catalysis.* 2007;6:1-17.
23. Fesenko EA, Barnes PA, Parkes GMB. SCTA and catalysis. In: Sørensen OT, Rouquerol J, editors. *Sample controlled thermal analysis: Origin, goals, multiple form and future*: Kluwer Academic; 2003. p. 174-225.
24. Llewellyn P, Rouquerol F, Rouquerol J. SCTA and adsorbents. In: Sørensen OT, Rouquerol J, editors. *Sample controlled thermal analysis: Origin, goals, multiple form and future*. Dordrecht: Kluwer Academic; 2003. p. 135-73.
25. Alcalá MD, Criado JM, Gotor FJ, Real C. Beta-sialon obtained from carbothermal reduction of kaolinite employing sample controlled reaction temperature (SCRT). *J Mater Sci.* 2006 Apr;41(7):1933-8.
26. Alcalá MD, Criado JM, Real C. Sample controlled reaction temperature (SCRT): Controlling the phase composition of silicon nitride obtained by carbothermal reduction. *Advanced Engineering Materials.* 2002 Jul;4(7):478-82.
27. Alcalá MD, Gotor FJ, Pérez-Maqueda LA, Real C, Dianez MJ, Criado JM. Constant rate thermal analysis (CRTA) as a tool for the synthesis of materials with controlled texture and structure. *J Therm Anal Calorim.* 1999;56(3):1447-52.
28. Real C, Alcalá D, Criado JM. Synthesis of silicon carbide whiskers from carbothermal reduction of silica gel by means of the constant rate thermal analysis (crtA) method. *Solid State Ionics.* 1997 Feb;95(1-2):29-32.
29. Monnereau O, Tortet L, Llewellyn P, Rouquerol F, Vacquier G. Synthesis of Bi₂O₃ by controlled transformation rate thermal analysis: A new route for this oxide? *Solid State Ionics.* 2003 Feb;157(1-4):163-9.
30. Criado JM, Gotor FJ, Real C, Jiménez F, Ramos S, Delcerro J. Application of the constant rate thermal-analysis technique to the microstructure control of BaTiO₃ yielded from coprecipitated oxalate. *Ferroelectrics.* 1991;115(1-3):43-8.
31. Gotor FJ, Pérez-Maqueda LA, Criado JM. Synthesis of BaTiO₃ by applying the sample controlled reaction temperature (SCRT) method to the thermal decomposition of barium titanate oxalate. *J Eur Ceram Soc.* 2003 Mar;23(3):505-13.
32. Pérez-Maqueda LA, Dianez MJ, Gotor FJ, Sayagues MJ, Real C, Criado JM. Synthesis of needle-like BaTiO₃ particles from the thermal decomposition of a citrate precursor

- under sample controlled reaction temperature conditions. *J Mater Chem.* 2003;13(9):2234-41.
- 1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
33. Arii T, Terayama K, Fujii N. Controlled-rate thermal analysis - study of the process of super hard material debinding. *J Therm Anal.* 1996 Dec;47(6):1649-61.
 34. Dwivedi A, Speyer RF. Rate-controlled organic burnout of multilayer green ceramics. *Thermochim Acta.* 1994 Dec;247(2):431-8.
 35. Nishimoto MY, Speyer RF, Hackenberger WS. Thermal processing of multilayer plzt actuators. *J Mater Sci.* 2001;36(9):2271-6.
 36. Paulik J, Paulik F. Simultaneous thermoanalytical examinations by means of derivatograph. Wilson's, comprehensive analytical chemistry. XII. Amsterdam: Elsevier; 1981.
 37. Paulik F. Special trends in thermal analysis. New York: John Wiley; 1995.
 38. Parkes GMB, Barnes PA, Charsley EL. New concepts in sample controlled thermal analysis: Resolution in the time and temperature domains. *Anal Chem.* 1999 Jul;71(13):2482-7.
 39. Sanchez-Jimenez PE, Perez-Maqueda LA, Crespo-Amoros JE, Lopez J, Perejon A, Criado JM. Quantitative characterization of multicomponent polymers by sample-controlled thermal analysis. *Anal Chem.* 2010 Nov 1;82(21):8875-80.
 40. Arii T, Kishi A. The effect of humidity on thermal process of zinc acetate. *Thermochim Acta.* 2003 Apr;400(1-2):175-85.
 41. Bordere S, Floreancig A, Rouquerol F, Rouquerol J. Obtaining a divided uranium oxide from the thermolysis of $\text{UO}_2(\text{NO}_3) \cdot 2.6\text{H}_2\text{O}$ - outstanding role of the residual pressure. *Solid State Ionics.* 1993 Sep;63-5:229-35.
 42. Bordere S, Rouquerol F, Llewellyn PL, Rouquerol J. Unexpected effect of pressure on the dehydration kinetics of uranyl nitrate trihydrate: An example of a smith-topley effect. *Thermochim Acta.* 1996 Jul;283:1-11.
 43. Criado JM, Perez-Maqueda LA, Gotor FJ, Malek J, Koga N. A unified theory for the kinetic analysis of solid state reactions under any thermal pathway. *J Therm Anal Calorim.* 2003;72(3):901-6.
 44. Koga N, Criado JM, Tanaka H. Kinetic analysis of the thermal decomposition of synthetic malachite by crta. *J Therm Anal Calorim.* 2000;60(3):943-54.
 45. Koga N, Criado JM, Tanaka H. A kinetic aspect of the thermal dehydration of dilithium tetraborate trihydrate. *J Therm Anal Calorim.* 2002;67(1):153-61.
 46. Laureiro Y, Jerez A, Rouquerol F, Rouquerol J. Dehydration kinetics of wyoming montmorillonite studied by controlled transformation rate thermal analysis. *Thermochim Acta.* 1996 May;278:165-73.
 47. Ortega A, Roldan MA, Real C. Carbothermal synthesis of vanadium nitride: Kinetics and mechanism. *Int J Chem Kinet.* 2006 Jun;38(6):369-75.
 48. Parkes GMB, Barnes PA, Charsley EL, Reading M, Abrahams I. Real-time analysis of peak shape: A theoretical approach to sample controlled thermal analysis. *Thermochim Acta.* 2000 Jul;354(1-2):39-43.
 49. Tatsuoka T, Koga N. Effect of atmospheric water vapor on the thermally induced crystallization in zirconia gel. *J Am Ceram Soc.* 2012 Feb;95(2):557-64.
 50. Tiernan MJ, Barnes PA, Parkes GMB. Use of solid insertion probe mass spectrometry and constant rate thermal analysis in the study of materials: Determination of apparent activation energies and mechanisms of solid-state decomposition reactions. *J Phys Chem B.* 1999 Aug;103(33):6944-9.
 51. Tiernan MJ, Barnes PA, Parkes GMB. New approach to the investigation of mechanisms and apparent activation energies for the reduction of metal oxides using constant reaction rate temperature-programmed reduction. *J Phys Chem B.* 1999 Jan;103(2):338-45.

- 1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
52. Yamada S, Tsukumo E, Koga N. Influences of evolved gases on the thermal decomposition of zinc carbonate hydroxide evaluated by controlled rate evolved gas analysis coupled with TG. *J Therm Anal Calorim.* 2009 Feb;95(2):489-93.
 53. Criado JM, Perez-Maqueda LA. Sample controlled thermal analysis and kinetics. *J Therm Anal Calorim.* 2005;80(1):27-33.
 54. Sanchez-Jimenez PE, Criado JM, Perez-Maqueda LA. Kissinger kinetic analysis of data obtained under different heating schedules. *J Therm Anal Calorim.* 2008;94(2):427-32.
 55. Sanchez-Jimenez PE, Perez-Maqueda LA, Perejon A, Criado JM. Combined kinetic analysis of thermal degradation of polymeric materials under any thermal pathway. *Polym Degrad Stab.* 2009 Nov;94(11):2079-85.
 56. Sanchez-Jimenez PE, Perejon A, Criado JM, Diane MJ, Perez-Maqueda LA. Kinetic model for thermal dehydrochlorination of poly(vinyl chloride). *Polymer.* 2010 Aug;51(17):3998-4007.
 57. Sanchez-Jimenez PE, Perez-Maqueda LA, Perejon A, Criado JM. A new model for the kinetic analysis of thermal degradation of polymers driven by random scission. *Polym Degrad Stab.* 2010 May;95(5):733-9.
 58. Sanchez-Jimenez PE, Perez-Maqueda LA, Perejon A, Criado JM. Generalized kinetic master plots for the thermal degradation of polymers following a random scission mechanism. *J Phys Chem A.* 2010 Aug;114(30):7868-76.
 59. Sanchez-Jimenez PE, Perez-Maqueda LA, Perejon A, Criado JM. Constant rate thermal analysis for thermal stability studies of polymers. *Polym Degrad Stab.* 2011 May;96(5):974-81.
 60. Sanchez-Jimenez PE, Perez-Maqueda LA, Perejon A, Criado JM. Nanoclay nucleation effect in the thermal stabilization of a polymer nanocomposite: A kinetic mechanism change. *J Phys Chem C.* 2012 May;116(21):11797-807.
 61. Criado JM, Perez-Maqueda LA. Scta and kinetics. In: Sørensen OT, Rouquerol J, editors. *Sample controlled thermal analysis: Origin, goals, multiple form and future.* Dordrecht Kluwer Academic; 2003.
 62. Criado JM. Kinetic-analysis of thermoanalytical diagrams obtained with the quasi-isothermal heating technique. *Thermochim Acta.* 1979;28(2):307-12.
 63. Criado JM, Ortega A, Gotor F. Correlation between the shape of controlled-rate thermal-analysis curves and the kinetics of solid-state reactions. *Thermochim Acta.* 1990 Jan;157(1):171-9.
 64. Reading M. Controlled rate thermal analysis and beyond. In: Charsley EL, Warrington SB, editors. *Thermal analysis -techniques and applications: Royal Society of Chemistry;* 1992. p. 126-55.
 65. Rouquerol J. Critical examination of several problems typically found in kinetic study of thermal-decomposition under vacuum. *J Therm Anal.* 1973;5(2-3):203-16.
 66. Diane MJ, Perez-Maqueda LA, Criado JM. Direct use of the mass output of a thermobalance for controlling the reaction rate of solid-state reactions. *Rev Sci Instrum.* 2004 Aug;75(8):2620-4.
 67. Rouquerol F, Rouquerol J. Thermal analysis. In: Wiedemann HG, editor. *Thermal analysis proc 3rd icta, 19711972.* p. 373.
 68. Perez-Maqueda LA, Criado JM, Sanchez-Jimenez PE. Combined kinetic analysis of solid-state reactions: A powerful tool for the simultaneous determination of kinetic parameters and the kinetic model without previous assumptions on the reaction mechanism. *J Phys Chem A.* 2006 Nov;110(45):12456-62.
 69. Perejon A, Sanchez-Jimenez PE, Criado JM, Perez-Maqueda LA. Kinetic analysis of complex solid-state reactions. A new deconvolution procedure. *J Phys Chem B.* 2011 Mar 3;115(8):1780-91.
 70. Hammer A. User com. Information for users of Mettler-Toledo thermal analysis systems nº 35. June 2012.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

71. Wang FCY, Burleson AD. The development of pyrolysis fast gas chromatography for analysis of synthetic polymers. *Journal of Chromatography A*. 1999 Feb;833(1):111-9.

72. Peris-Vicente J, Baumer U, Stege H, Lutzenberger K, Adelantado JVG. Characterization of commercial synthetic resins by pyrolysis-gas chromatography/mass spectrometry: Application to modern art and conservation. *Anal Chem*. 2009 Apr;81(8):3180-7.

Captions of figures

1
2
3 Fig. 1. Curves obtained under high vacuum at a linear heating rate of 0.5 K min^{-1}
4 for 4.5 mg (a) and 1.9 mg (b) of PbCO_3 .
5
6

7 Fig. 2. CRTA curve of PbCO_3 obtained under high vacuum at a constant
8 decomposition rate $C = 1.6 \cdot 10^{-3} \text{ min}^{-1}$. The superimposed black points have
9 been taken from the part of the cyclic CRTA experiment that is running at $C =$
10 $1.6 \cdot 10^{-3} \text{ min}^{-1}$.
11
12

13
14 Fig. 3. A tooth in a cyclic CRTA for PbCO_3 , showing the evolution of temperature
15 and mass loss. Values of T_1 and T_2 corresponding to the C_1 and C_2 reaction rates
16 have been marked in the figure.
17
18

19
20 Fig. 4. CRTA curve resulting from the thermal dehydrochlorination of PVC sample
21 at a constant reaction rate of $6 \cdot 10^{-3} \text{ min}^{-1}$. Experimental curve is represented by
22 points while the theoretical reconstructed one is represented by a line.
23
24

25
26
27 Fig. 5 Experimental mass loss against temperature recorded under flowing
28 nitrogen atmosphere at a constant reaction rate of $3 \cdot 10^{-3} \text{ min}^{-1}$ for a blend PVC-
29 DINCH (solid line). The linear heating rate experiment recorded at 1 K min^{-1} has
30 been included for comparison (dotted line).
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65




Figure 1.




Figure 2

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65




Figure 3




Figure 4

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65




Figure 5

Copyright Transfer Statement

Publisher: Akadémiai Kiadó Zrt., Budapest, Hungary

The signed Copyright Transfer Statement please return to:
<http://www.editorialmanager.com/jtac/>

Author

Name: LUIS A. PEREZ MAQUEDA
Address: JCM SE
E-mail address: maqueda@cica.es

Article information

Title: KINETIC STUDIES IN SOLID STATE REACTIONS BY
Journal title: Journal of Thermal Analysis and Calorimetry
Co-authors: J.M. CRIADO, PE. SANCHEZ-JIMENEZ, A. PEREZ JON

I. Transfer of copyright

By execution of the present Statement Author transfers copyright and assigns exclusively to Publisher all rights, title and interest that Author may have (for the extent transferable) in and to the Article and any revisions or versions thereof, including but not limited to the sole right to print, publish and sell the Article worldwide in all languages and media. Transfer of the above rights is referred to as those of the final and published version of the Article but does not restrict Author to self-archive the preprint version of his/her paper (see Section III).

II. Rights and obligations of Publisher

The Publisher's rights to the Article shall especially include, but shall not be limited to:

- ability to publish an electronic version of the Article via the website of the publisher Akadémiai Kiadó, www.akademiai.com (in Hungary), as well as the co-publisher's website, www.SpringerLink.com (outside of Hungary) or any other electronic format or means of electronic distribution provided by or through Akadémiai Kiadó or Springer from time to time, selling the Article world-wide (through subscriptions, Pay-per-View, single archive sale, etc.)
- transforming to and selling the Article through any electronic format
- publishing the Article in the printed Journals as listed on the official Website of Publisher
- transferring the copyright and the right of use of the Article onto any third party
- translating the Article
- taking measures on behalf of the Author against infringement, inappropriate use of the Article, libel or plagiarism.

Publisher agrees to send the text of the Article to the e-mail address of Author indicated in the present Statement for preview before the first publishing either in paper and/or electronic format (Proof). Author shall return the corrected text of the Article within 2 days to the Publisher. Author shall, however, not make any change to the content of the Article during the First Proof preview.

III. Rights and obligations of Author


The Author declares and warrants that he/she is the exclusive author of the Article – or has the right to represent all co-authors of the Article (see Section IV) – and has not granted any exclusive or non-exclusive right to the Article to any third party prior to the execution of the present Statement and has the right therefore to enter into the present Statement and entitle the Publisher the use of the Article subject to the present Statement. By executing the present Statement Author confirms that the Article is free of plagiarism, and that Author has exercised reasonable care to ensure that it is accurate and, to the best of Author's knowledge, does not contain anything which is libelous, or obscene, or infringes on anyone's copyright, right of privacy, or other rights. The Author expressly acknowledges and accepts that he/she shall be entitled to no royalty (or any other fee) related to any use of the Article subject to the present Statement. The Author further accepts that he/she will not be entitled to dispose of the copyright of the final, published version of the Article or make use of this version of the Article in any manner after the execution of the present Statement. The Author is entitled, however, to self-archive the preprint version of his/her manuscript. The preprint version is the Author's manuscript or the galley proof or the Author's manuscript along with the corrections made in the course of the peer review process. The Author's right to self-archive is irrespective of the format of the preprint (.doc, .tex, .pdf) version and self-archiving includes the free circulation of this file via e-mail or publication of this preprint on the Author's webpage or on the Author's institutional repository with open or restricted access. When self-archiving a paper the Author should clearly declare that the archived file is not the final published version of the paper, he/she should quote the correct citation and enclose a link to the published paper ([http://dx.doi.org/\[DOI of the Article without brackets\]](http://dx.doi.org/[DOI of the Article without brackets])).

IV. Use of third party content as part of the Article

When not indicating any co-authors in the present Statement Author confirms that he/she is the exclusive author of the Article. When indicating co-authors in the present Statement Author declares and warrants that all co-authors have been listed and Author has the exclusive and unlimited right to represent all the co-authors of the Article and to enter into the present Statement on their behalf and as a consequence all declarations made by Author in the present Statement are made in the name of the co-authors as well. Author also confirms that he/she shall hold Publisher harmless of all third-party claims in connection to non-authorized use of the Article by Publisher. Should Author wish to reuse material sourced from third parties such as other copyright holders, publishers, authors, etc. as part of the Article, Author bears responsibility for acquiring and clearing of the third party permissions for such use before submitting the Article to the Publisher for acceptance. Author shall hold Publisher harmless from all third party claims in connection to the unauthorized use of any material under legal protection forming a part of the Article.

V. Other provisions

Subject to the present Statement the Article shall be deemed as first published within the Area of the Hungarian Republic. Therefore the provisions of the Hungarian law, especially the provisions of Act LXXVI of 1999 on Copy Rights shall apply to the rights of the Parties with respect to the Article. For any disputes arising from or in connection with the present Statement Parties agree in the exclusive competence of the Central District Court of Pest or the Capital Court of Budapest respectively.

.....
Author	Signature	Date and Place
LUIS A PEREZ MAQUEDA		31/10/2012