

1 Effects of the presence of Fe(0) on the sorption of lanthanum and lutetium
2 mixtures in smectites

3 Evgeny Galunin^a, María D. Alba^{b,*}, Maria J. Santos^c, Miquel Vidal^a

4 ^a *Departament de Química Analítica, Universitat de Barcelona, Martí i Franqués 1-11, 08028 Barcelona, Spain.*

5 ^b *Instituto de Ciencia de Materiales de Sevilla, Consejo Superior de Investigaciones Científicas - Universidad de
6 Sevilla, Av. Américo Vespucio 49, 41092 Sevilla, Spain.*

7 ^c *Departamento de Química, Universidade Estadual de Londrina, Londrina, PR, 86051-990, Brazil.*

8

9 Correspondence author: Tel.: (+34) 954489546; Fax: (+34) 954460665; email: alba@icmse.csic.es

10

11 **ABSTRACT**

12 The sorption of La and Lu mixtures was examined in two bentonites after incubation
13 for three months at 20 and 80°C with Fe(0), as a laboratory approach to evaluate the effects of
14 waste canister corrosion in a deep repository on the performance of clay engineered barriers.
15 The sorption/desorption parameters were determined from batch tests in two ionic media:
16 deionized water and, to consider the additional effect of cement leachates, 0.02 mol L⁻¹ Ca.

17 Results from XRD analyses showed the formation of crystalline FeO(OH), goethite, in
18 a few samples and the degradation of the bentonites due to Fe(0) oxidation during incubation.
19 Moreover, the EDX spectra showed that the lanthanides were sorbed primarily at smectite
20 sites, although sorption onto goethite was also observed, whereas Fe(0) particles did not
21 contribute to lanthanide sorption. The formation of goethite could explain the high K_d values
22 measured in a few scenarios (e.g., those with single solutions or mixtures with the lowest
23 initial concentration of the competitive lanthanide in which high affinity sites governed
24 sorption), with up to 3-fold increases over the values obtained without Fe incubation.
25 However, at higher lanthanide concentration, K_d values decreased or remained constant
26 compared to the samples without Fe incubation, which could be explained by bentonite
27 degradation. In the Ca medium, as much as 5 times lower K_d values were obtained, because of
28 the competitive effect of the Ca ions, especially for Lu in the MX80 bentonite. This indicated
29 that the small number of high affinity sites had been diminished.

30 The sorption data were satisfactorily fitted to a two-solute Langmuir model. In
31 addition, K_d values correlated well with desorption data, which showed that the larger the
32 decrease in K_d, the larger the increase in sorption reversibility. It is suggested that corrosion
33 products from the metal canister might compromise the long-term radionuclide retention of
34 the clay-engineered barriers.

35 **1. Introduction**

36

37 A deep geological repository (DGR), designed for the long-term management of radioactive
38 waste, is a multi-barrier system consisting of engineered and backfill barriers surrounded by an
39 additional geosphere barrier (McCombie et al., 2000; Astudillo, 2001; Chapman, 2006). Engineered
40 barriers are commonly constructed with bentonite due to its low hydraulic conductivity and
41 diffusivity and its high cation sorption capacity and buffering properties (Meunier et al., 1998;
42 Landais, 2006; Pusch, 2006). In addition, bentonite retards the diffusion of radionuclides through
43 sorption processes, and it is able to react with the radioactive leachate (Coppin et al., 2002;
44 Bradbury and Baeyens, 2005). However, the effectiveness of these clay-engineered barriers, which
45 are located between the metal container storing the spent nuclear fuel and the external concrete
46 barriers, may be compromised by the buildup of degradation products, such as iron resulting from
47 the corrosion of the metal canister or alkaline calcium-enriched leachates from the concrete barriers
48 (Metcalf and Walker, 2004; Kumpulainen et al., 2010).

49 Smectites, the main constituents of bentonite, react chemically with iron, which alters their
50 properties (Lantenois et al., 2005; Wilson et al., 2006a, 2006b; Perronet et al., 2007; Anastácio et
51 al., 2008; Bennett and Gens, 2008). Under the conditions expected in the repository, alteration of
52 smectite would most likely increase hydraulic conductivity and porosity/permeability and decrease
53 its swelling pressures and cation exchange capacity (CEC) (Bildstein et al., 2006; Carlson et al.,
54 2007; Gaudin et al., 2009; Savage et al., 2010). The mineralogical changes leading to the
55 destabilization of the smectite structure as a result of the formation of corrosion products such as
56 magnetite, hematite, goethite and serpentine-like minerals have also been investigated (Smart et al.,
57 2002; Lantenois et al., 2005; Bildstein et al., 2006; Carlson et al., 2007; Gaudin et al., 2009).
58 However, corrosion products from metal canister degradation may also contribute to the retardation
59 of radionuclide transport upon release from the waste canister (Viani et al., 1997).

60 Because there is still a lack of data concerning the direct effects of the presence of Fe on
61 radionuclide sorption in smectites, here we study the effect of Fe(0) on the sorption/desorption
62 pattern of a lanthanide mixture in two smectites that have previously been used in investigations
63 dealing with clay-engineered barriers, the MX80 and FEBEX bentonites. Lanthanum and lutetium,
64 were used as trivalent actinide analogues due to their chemical similarity (Chapman and Smellie,
65 1986; Buil et al., 2007). Sorption experiments were carried out after incubation of the bentonites for
66 90 days at two temperatures, 20 and 80°C (the latter simulating DGR conditions), in the presence of
67 Fe(0) (Lantenois, 2003; Perronet et al., 2007). Sorption experiments were conducted in pure water
68 and in a Ca-enriched aqueous solution, to simulate the role of cement leachates in lanthanide
69 sorption. Sorption data were fitted with a two-solute Langmuir equation to facilitate the comparison
70 of the scenarios examined. Last, sorption reversibility was estimated from desorption tests and was
71 compared with the sorption pattern.

72

73 **2. Materials and Methods**

74

75 *2.1. Smectite samples*

76

77 The FEBEX and MX80 bentonites which were used in this study have been extensively
78 investigated in the recent past in many countries (Tripathy et al., 2004). The main initial
79 characteristics of the clays (Fernandez et al., 2004; Montes-H et al., 2007) are summarized in Table
80 1. MX80 bentonite contains more monovalent cations than bivalent cations, whereas the opposite is
81 valid for FEBEX bentonite. The layer charge of the smectite present is 0.76 e/uc and 1.19e/uc
82 respectively for the MX80 and FEBEX bentonite respectively, yielding a higher cation exchange
83 capacity for the FEBEX bentonite.

84 In all the samples, the < 2 µm fraction was separated by sedimentation and carbonates and
85 organic matter were eliminated to ensure purity.

86

87 *2.2. Sample pretreatment*

88

89 Before the sorption experiments, sets of 0.2 g of the bentonite samples were incubated in
90 sealed tubes with 0.07 g of metallic iron powder (99.98%, Merck) for 90 days at either 20 or 80°C
91 in the presence of 5 mL of the aqueous phase in which the subsequent sorption would take place
92 (deionized water or Ca solution). The pH during the incubation period was neutral or slightly basic,
93 accordingly to the smectite initial pH (see Table 1). Oxygen was displaced by N₂ both in the
94 solutions and in the resulting suspensions in the beginning of the incubation period. The
95 temperatures and clay/Fe mass ratios used were assumed to simulate conditions in a DGR
96 (Lantenois, 2003; Perronet et al., 2007).

97

98 *2.3. Sorption/desorption experiments*

99

100 Batch sorption tests were carried out in 50 mL centrifuge tubes by adding 30 mL solution
101 containing mixtures of lanthanides with various ratios in two different ionic media to the previously
102 incubated bentonites. The ionic media were either deionized water (Milli-Q Reagent Water System
103 from Millipore, resistivity of >18 MΩ cm⁻¹) or 0.02 mol L⁻¹ Ca(NO₃)₂ aqueous solution (Prolabo,
104 RP Normapur, analytical grade) at an initial pH of 7, and the concentrations of the theoretical initial
105 La and Lu concentrations used in the solutions are shown in Table 2. The lanthanide solutions were
106 prepared from La(NO₃)₃ and Lu(NO₃)₃ (99.9%, Aldrich). The experimental design provided
107 sorption isotherms of the primary lanthanide with a fixed concentration of the competitive
108 lanthanide. The suspensions were shaken end-over-end at 30 rpm at room temperature for 24 h and
109 subsequently were centrifuged at 10,000 rpm for 25 min (Hettich Universal 30 F with an E1174
110 rotor) and filtered (Whatman 41, 0.22 μm). The supernatants were collected in polyethylene bottles,
111 diluted with 1% HNO₃ and stored at 4°C for analysis.

112 Batch desorption tests were performed the day after the sorption tests by bringing the clay
113 residues from the sorption tests into contact with the two ionic media mentioned above, but without
114 the lanthanides. The other experimental conditions were identical to those described for the sorption
115 tests.

116

117 *2.4. Structural characterization methods*

118 *2.4.1. X-Ray Diffraction (XRD).*

119 Powder X-ray diffraction data were collected with a Bruker D8 Advance diffractometer with
120 CuK α 1 radiation ($\lambda=1.5405 \text{ \AA}$) and a Ni filter. The diffractograms were obtained from 3° to $70^\circ 2\theta$
121 with a step of 0.05° and a counting time of 3 s. Before carrying out the measurements, the zero of
122 the instrument was calibrated following equipment recommendations. Peak positions were
123 controlled with Rietveld fitting using corundum as reference sample. The crystalline phases were
124 identified using the computer program X'Pert HighScore (Philips Analytical B.V. Almelo, The
125 Netherlands).

126

127 *2.4.2. Scanning electron microscopy (SEM) and energy dispersion X-ray (EDX) analyses.*

128 The morphology of the samples was analyzed by SEM (JEOL, Model JSM 5400) at 20 kV.
129 An EDX system (Oxford Link ISIS) was fitted to the SEM equipment to perform chemical analyses
130 of the samples using a Si/Li detector with a Be window.

131

132 *2.5. Determination of La and Lu in the solutions derived from sorption/desorption experiments*

133

134 Lanthanide concentrations in the initial solutions and in the supernatants obtained after the
135 sorption/desorption experiments were analyzed by Inductively Coupled Plasma-Optical Emission
136 Spectrometry (ICP-OES) (Perkin-Elmer Optima-3200RL). The wavelengths (nm) used in the ICP-
137 OES measurements were 384.902 (La), 261.542 (Lu), 259.939 (Fe) and 317.933 (Ca).

138 Concentration ranges of the standards were 0.05–100 mg L⁻¹ for La and 0.01–100 mg L⁻¹ for Lu.
139 The detection limits for the ICP-OES are 50 µg L⁻¹ for La, 10 µg L⁻¹ for Lu and Fe and 200 µg L⁻¹
140 for Ca.

141

142 2.6. Calculation of sorption/desorption parameters

143

144 Following ICP-OES measurements, the initial lanthanide concentration (C_{init} , meq L⁻¹), the
145 equilibrium concentration in the supernatant after sorption experiments (C_{eq} , meq L⁻¹) and the
146 equilibrium concentration in the supernatant after desorption experiments ($C_{eq,des}$, meq L⁻¹) were
147 determined. Based on these data, the following parameters were calculated.

148

149 a) The sorption distribution coefficient (K_d , L kg⁻¹) (equation 1):

$$150 \quad K_d = \frac{(C_{init} - C_{eq})V}{C_{eq} m} \quad (1)$$

151 where V is the liquid phase volume in L and m is the clay sample weight in kg.

152

153 b) The desorption distribution coefficient ($K_{d,des}$, L kg⁻¹) (equation 2):

$$154 \quad K_{d,des} = \frac{(C_{init} - C_{eq} - C_{eq,des})V}{C_{eq,des} m} \quad (2)$$

155

156 c) The desorption rate (R_{des} , %) (equation 3):

$$157 \quad R_{des} = \frac{C_{eq,des}}{C_{init} - C_{eq}} 100 \quad (3)$$

158

159 2.7. Use of the two-solute Langmuir equation to fit sorption data

160

161 The Langmuir model was chosen to fit the sorption data. This model assumes that sorption
162 takes place at specific homogeneous sites, that the sorbent forms a monolayer, that interactions
163 between sorbed species do not take place, and that the sorption energy is constant over the entire
164 surface (Do, 1998). An extended form of the Langmuir model, shown in equation (4), was used to
165 analyze the two-solute sorption (Srivastava et al., 2006; Sanghwa et al., 2009). This equation
166 predicts the concentration of solute i sorbed ($C_{sorb,i}$) in the presence of sorption-competitive solutes.

$$167 \quad C_{sorb,i} = \frac{b_i K_i C_{eq,i}}{1 + \sum_{j=1}^N K_j C_{eq,j}} \quad (4)$$

168 In equation (4), $C_{eq,i}$ is the equilibrium concentration of solute i in a mixture of N solutes, and b_i and
169 K_i are empirical sorption parameters obtained from the fitting of the isotherms. The former
170 represents the maximum sorption capacity determined by the reactive surface sites in an ideal
171 monolayer system, and the latter represents the bonding energy associated with a pH-dependent
172 equilibrium constant. In addition, we plotted the sorption data in three-dimensional space, because
173 the three-dimensional fitting added information to that of the two-dimensional fitting (Yan et al.,
174 2010).

175

176 2.8. Data handling

177

178 The sorption/desorption tests were performed in 3-6 replicates, which allowed the
179 calculation of the mean and standard deviations of the derived parameters. The sorption data fittings
180 were made using *sftool* (an interactive environment for fitting curves to n-dimensional data), which
181 is included in the mathematical software Matlab 7.10.0 (Mathworks, 2010). The fitting coefficients
182 were taken for positive values with confidence limits $\geq 95\%$ using non-linear least squares fitting
183 with the Trust-region or Levenberg-Marquardt algorithm option. In all fittings, the fit values (R^2)
184 were close to 1 with low residual mean square error (RMSE).

185

186 **3. Results and Discussion**

187
188 *3.1. Structural analyses of samples resulting from sorption experiments*

189
190 The XRD patterns of the FEBEX and MX-80 samples are shown in Figs. 1 and 2. Two sets
191 of reflections could be distinguished in the Fe-treated bentonites, one because of the iron phases and
192 one a result of the modified bentonites. Crystalline Fe is the most abundant iron phases phase in all
193 samples (F in the XRD patterns). Small amounts of goethite were also observed (Bildstein, 2006;
194 Carlson, 2007). It is considered that amorphous Fe oxyhydroxides may also be present and may
195 contribute to the observed increase of background.

196 Swelling of the bentonite layers was observed in the two bentonites. Specifically, the 001
197 space increased from 14.7 Å to 15.5 Å in FEBEX and from 12.0 Å to 15.4 Å in MX-80, suggesting
198 sorption of hydrated M^{3+} cations in the interlayer space (Alba et al., 2001). The 060 reflection of
199 Fe-treated FEBEX shifted to higher 2θ values, which indicated lower b-spacing due to the creation
200 of a vacant site in the octahedral sheet and the subsequent leaching of the octahedral cations (Grim,
201 1968). Additionally, high background was observed in both bentonites due to amorphous phases
202 and clay collapse (d_{001} ca. 9 Å marked with an asterisk in the XRD patterns) or due to fluorescence
203 from Fe, which was evident when Cu radiation was used. Lantenois et al. (2005) had already
204 assessed the destabilization of trioctahedral smectites at pH higher than 7 in contact with metallic
205 Fe at representative temperatures of nuclear waste disposal (i.e., 80°C). Similarly, dioctahedral
206 smectites were destabilized under such conditions and exhibited lower swelling pressures and
207 reduced CEC (Carlson et al., 2007; Sanders et al., 2010). The bentonites tested here were mainly
208 constituted by dioctahedral smectites, which have already been observed as being less stable than
209 the trioctahedral members (Alba et al., 2001; Alba et al., 2010).

210 The SEM micrograph of FEBEX after Fe pretreatment is shown in Fig. 3a. Both lamellar
211 and spherical particles were observed, which are characteristic of smectites and metallic iron,

212 respectively (SEM micrograph of the initial metallic iron powder not shown). The presence of
213 spherical iron particles was confirmed by X-ray mapping (Fig. 3b). Finally, the La and Lu EDX
214 mapping (Figs. 3c and 3d) displayed a homogeneous distribution of La and Lu. Similar behavior
215 was observed for the rest of the scenarios examined.

216 The EDX spectra of the lamellar FEBEX and MX80 bentonite particles from samples which
217 were not submitted to Fe incubation (Figs. 4a and 6a) are typical of smectites. New lines were
218 observed in Figs. 4b-e and 6b-e, and they were due to the $L\alpha$ and $L\beta$ lines of La and Lu with
219 relative intensities consistent with their initial concentrations, which confirmed their sorption at
220 smectite sites. Finally, Figs. 4d-e and 6d-e showed a high intensity of the Ca-line that indicated a
221 competitive sorption of Ca when it was present in the sorption medium. The EDX spectra of the
222 spherical particles (Figs. 5 and 7) generally showed signals corresponding to the Fe $K\alpha$ and $K\beta$,
223 which did not indicate significant sorption of La and/or Lu in those particles. However in goethite
224 bearing samples (Bildstein, 2006; Carlson, 2007) (i.e., FEBEX incubated at 80°C with La/Lu ratio
225 0.09/3.0 in the Ca medium, or MX80 incubated at 80°C with La/Lu ratio 0.09/3.0 in water medium),
226 the EDX spectra (Figs. 5c and 7a, respectively) displayed spectral lines of La and Lu, thus
227 demonstrating that lanthanides were also sorbed at the new Fe phases formed by Fe oxidation. This
228 was consistent with reported data that showed that the amorphous species of oxidized iron were
229 able to sorb lanthanides onto their surface, and that the equilibrium constant for sorption depended
230 on the nature of the lanthanide (Quinn et al 2006).

231

232 3.2. Examination of lanthanide sorption data

233

234 The sorption data for La and Lu in the two media for FEBEX and MX80 bentonites,
235 including the lanthanide initial (C_{init} (La), C_{init} (Lu)) and sorbed concentrations (C_{sorb} (La), C_{sorb}
236 (Lu)) and the resulting pH in the supernatants following sorption are summarized in Tables 3 and 4.
237 The Fe concentration in the equilibrium solution following sorption experiments varied within a

238 range of 0.01 – 0.16 meq L⁻¹ for samples incubated at 20°C. For samples incubated at 80°C, Fe
239 concentrations were generally similar, although the Fe concentration in the water medium
240 occasionally exceeded 1 meq L⁻¹.

241 Lanthanide sorption was systematically higher in the FEBEX than in the MX80 bentonite in
242 the water medium, especially at the low-medium concentration range, whereas this effect was not
243 statistically significant in the Ca medium. Since the smectites in the two bentonites are dioctahedral,
244 other factors such as the smectite CEC, the sorption pH and the type of isomorphic substitutions
245 may be considered to affect lanthanide sorption. Previous studies that examined lanthanide sorption
246 in set of six smectites showed that, for smectites with similar structure, the type of isomorphic
247 substitutions and, especially, sorption pH controlled the sequence of lanthanide sorption (higher
248 sorption at higher pH values), as these two latter factors affect the availability of sorption specific
249 sites in the smectites (Galunin et al., 2010). In contrast the CEC affected basically the ionic
250 exchange process, which is the driving force mechanism in the medium-large concentration range in
251 the water medium and in the whole range of lanthanide concentrations in the Ca medium (Galunin
252 et al., 2010). As the CEC values were sufficiently large, differences in sorption were not observed
253 here between smectites in the latter experimental setup. Regarding the role of pH, in the Ca medium,
254 since the initial pH was 7 to ensure that there were not solubility problems in the lanthanide higher-
255 concentration range, the final pH after the sorption experiments was similar for both bentonites, within
256 a narrow range of 6.1-6.4. In the case of the water medium, the pH of the sorption experiments with the
257 FEBEX bentonite was 6.2-7.5, depending of the final equilibrium lanthanide concentration, whereas
258 the pH with the MX80 bentonite experiments was lower (4.7-6.9).

259 In experiments with the water medium, there was a general decrease in the K_d values of a
260 given lanthanide with increasing initial concentrations in the range tested (from around 0.1 to 9 meq
261 L⁻¹) at a constant concentration of the competitive lanthanide. The decrease observed was
262 sometimes greater by two orders of magnitude, as was the case with La in the FEBEX smectite after
263 incubation at 80°C. This finding was similar to what was previously observed in these bentonites

264 without Fe pretreatment (Galunin et al., 2010, 2011). Changes in K_d due to the variation of the
265 initial lanthanide concentration were higher than previously reported as a result of changes in the
266 two clays tested and because of the incubation temperature. In addition, effects from the presence of
267 a competitive solute were also observed. At a constant concentration of a primary lanthanide, the
268 increase in concentration of the competitive lanthanide decreased the K_d of the primary lanthanide
269 by as much as two orders of magnitude. Again, this effect was stronger for La than for Lu,
270 especially in the FEBEX bentonite, suggesting a higher competitive effect of Lu over La as was
271 observed in previous reported experiments (Galunin et al., 2011).

272 The composition of the medium influenced K_d . Specifically, the K_d values in the Ca medium
273 were systematically lower compared to the water medium and also exhibited very little variance,
274 regardless of the initial concentration of lanthanide or clay. The decrease in K_d values from the
275 water to the Ca medium were nearly two orders of magnitude, especially in the FEBEX bentonite
276 when La was the target solute. The results corroborated previous data reported for the sorption of
277 mixtures of La and Lu in the absence of Fe (Galunin et al., 2011). The effect of Ca on the
278 quantification of K_d was explained in terms of the potential competitive influence of the Ca ions,
279 which were sorbed at the interlayer space and displaced the lanthanides to less specific sites because
280 the sorbed concentration of Ca was much higher than that of the two lanthanides (Galunin et al.,
281 2011).

282 As discussed above, the main sorption patterns observed in samples subjected to incubation
283 with Fe were similar to those already observed with smectites without Fe pretreatment. This
284 suggests that the main sorption mechanisms were similar, although the presence of Fe might
285 quantitatively affect the lanthanide sorption. On the one hand, the formation of oxidized iron
286 species, such as goethite, which has high sorption affinity (Dong et al., 2001; Quinn et al., 2006),
287 could contribute to a measurable increase in the K_d of the lanthanides. On the other hand, the likely
288 loss of efficacy in the bentonite performance due to the destabilization induced by Fe treatment, as
289 deduced from the structural analyses, could lead to a decrease in sorption sites with a high affinity

290 for lanthanides and thus to a decrease in K_d in certain scenarios. Therefore, the ratios of the K_d
291 values of the two lanthanides measured in the samples subjected to Fe treatment at both
292 temperatures versus the values determined under the same conditions but without Fe pretreatment,
293 were calculated to allow analysis of the effects of Fe incubation. The data used to calculate the
294 ratios were taken from previously reported experiments (Galunin et al., 2011). The K_d (La) for the
295 FEBEX bentonite samples incubated with Fe at 20°C in the water medium were higher than for
296 samples that had not been incubated with Fe in all the experiments with single La solutions and in
297 those within the low concentration range when Lu was also present. This indicates that further
298 increase in K_d was observed for the cases already having the highest K_d values. For the remaining
299 experimental setups K_d (La) decreased when the concentration of the competitive element increased
300 or was similar to K_d in the absence of Fe pretreatment. For Lu, although K_d (Lu) did not increase
301 after the Fe treatment, a similar decrease in K_d (Lu) was observed when the La concentration
302 increased. In all cases, the K_d values did not change after Fe treatment if the K_d of the lanthanides
303 was already low. These results indicate that when the number of high-affinity sorption sites was
304 high enough to specifically sorb the lanthanide present in the system (as was the case for
305 experiments with single lanthanide solutions or with low concentrations of either the primary or
306 secondary lanthanide), the Fe treatment led to an increase in K_d (Ln) due to the formation of Fe
307 oxides able to specifically sorb lanthanides. This potentially beneficial effect was discovered by
308 Viany et al., (1997) who suggested that the new Fe oxide phase could be an additional sorptive
309 phase for radionuclides. In our study, the formation of Fe oxides was minimal and the appearance of
310 new crystalline Fe oxide phases was observed in only a few samples, most likely because of the
311 short incubation time, although new amorphous phases were observed in all samples. Therefore,
312 because the formation of Fe oxides was low in our experiments, these sites became rapidly saturated
313 when the lanthanide concentration increased, and sorption was then limited by the smectite sites. As
314 Fe pretreatment caused smectite degradation when the lanthanide concentration increased, K_d
315 decreased following the saturation of specific sites, which were fewer than in the untreated

316 bentonites. In cases that were already governed by low affinity sites (e.g., at high initial
317 concentrations), Fe treatment did not affect lanthanide sorption.

318 These findings were also observed for the FEBEX samples treated at 80°C and in the MX80
319 bentonite at both temperatures. Notably, in the MX80 bentonite, the K_d ratios for Lu showed a
320 higher increase in K_d (Lu) at the lowest initial concentration range than that observed for the
321 FEBEX samples. In cases where sorption was completely or partially governed by the specific sites
322 in the bentonites, the K_d of the lanthanides tended to decrease after Fe pretreatment. However, in
323 those cases in which sorption was primarily controlled by low affinity sites, the K_d remained
324 relatively constant. Finally, the same trend was observed in the Ca medium. As Ca already acted as
325 a strong competitive solute for sorption, K_d values were low regardless of the Fe treatment.
326 However, there were significant K_d decrease that was not related to the lanthanide concentration.
327 Thus, it was suggested that in the Ca medium, because of the strong competitive effect of Ca and
328 the partial elimination of high affinity sites in the smectites, the low affinity sites were the only ones
329 responsible for lanthanide sorption, thus leading to a further general decrease in K_d .

330

331 *3.3. Use of a modified, two-solute Langmuir equation for the fitting of the sorption data*

332

333 A three-dimensional, two-solute Langmuir equation was applied to fit the sorption data. An
334 example of the 3-D Langmuir fitting was shown in Fig. 8, and the fitting parameters are
335 summarized in Table 5.

336 The values of the b parameter were similar to or slightly higher for Lu than for La in both
337 the water and Ca media, except in the case of the MX80 bentonite pretreated at 80°C in water
338 medium. The temperature of the Fe treatment did not have measurable effect on the b values. Thus,
339 the b values were consistent with the C_{sorb} values included in Tables 3 and 4 for the two lanthanides.
340 The b values were always lower than the CEC values of the bentonites, except in the case of MX80
341 bentonite pretreated at 80°C in the Ca medium. In this last case, the sorption isotherms in the Ca

342 medium did not indicate a maximum sorption capacity of the clays, thus they did not follow the
343 Langmuir sorption isotherm and the estimated b values were anomaly high and they exceeded the
344 CEC values of the bentonite.

345 The K parameters were much higher in the water than in the Ca medium, which was
346 consistent with higher K_d values found in the water medium. At both temperatures, $K_1(\text{Lu})$ was
347 higher than $K_1(\text{Lu})$ in the FEBEX bentonite in the water medium, whereas the opposite was
348 observed in the MX80 bentonite. This result was fully consistent with the K_d values measured
349 because $K_d(\text{La})$ was higher than $K_d(\text{Lu})$ in the FEBEX, but the opposite was true in the MX80
350 bentonite.

351 Assuming that a main objective of the Langmuir fitting is to allow comparisons with similar
352 systems, the obtained b and K_1 parameters were compared to those obtained from the sorption
353 fitting of samples not subjected to Fe pretreatment (Galunin et al., 2011). Ratios could not be
354 calculated because the b and K_i of the untreated samples originated from a more complete dataset,
355 but the b values obtained here were generally similar or lower than those obtained with the
356 untreated samples, thus indicating that the-Fe incubation seemed to provoke a decrease in the
357 sorption capacity of the Fe-incubated bentonites. In addition, although changes in the K_1 values
358 obtained in the Ca medium were hardly noticeable, the $K_1(\text{La})$ values obtained in the water
359 medium in the FEBEX bentonite were higher than in the untreated samples. This can be explained
360 by the influence of the $K_1(\text{La})$ in those cases where an increase in $K_d(\text{La})$ was measured (with K_d
361 ratios higher than 2) because they corresponded to experiments with the highest $K_d(\text{La})$. Instead,
362 the $K_1(\text{Lu})$ in the FEBEX samples decreased in the Fe-treated samples, consistent with the $K_d(\text{La})$
363 values. Regarding the MX80 samples, the K_1 values for La decreased. However, the K_1 values for
364 Lu increased; in accordance with the higher K_d ratios measured for Lu in the Fe-treated MX80
365 samples.

366

367 *3.4. Lanthanide sorption reversibility*

368

369 The desorption K_d values ($K_{d,des}$) and the desorption rates (R_{des}) for both lanthanides in the
370 Fe-treated bentonites are listed in Tables 6 and 7. As the two parameters are closely correlated
371 ($\log R_{des} = 2.99 - 0.74 \times \log K_{d,des}$, $R^2 = 0.81$ for La; $\log R_{des} = 2.92 - 0.74 \times \log K_{d,des}$, $R^2 = 0.74$ for
372 Lu), both parameters are equally valid to describe sorption reversibility. In the Fe-treated FEBEX
373 samples in the water medium, the R_{des} values for both lanthanides were lower than 4% even at the
374 highest initial concentrations, thus indicating that the sorption was virtually irreversible. In the
375 MX80 samples, desorption rates were higher, with a few values between 5 and 10% or higher. This
376 result indicates that lower K_d values are related to a higher sorption reversibility, thus confirming
377 that these were the scenarios with the lowest lanthanide retention by the smectite. Examination of
378 the values obtained in the Ca medium for the two bentonites confirmed this trend because the
379 desorption rates were higher than in the water medium, by more than 30% in the Fe-treated MX80
380 samples. Therefore, the lanthanide sorption in the Ca medium was not only lower but also more
381 reversible than in the water medium, as was also previously found for untreated samples (Galunin et
382 al., 2010). The results were consistent with previous reports that predicted significant sorption
383 reversibility due to the sorption of trivalent lanthanide cations at low affinity sites, in which the
384 sorption mechanisms are based on outer sphere processes such as ion-interlayer exchange (Bonnot-
385 Courtois and Jaffrezic-Renault, 1982; Coppin et al., 2003).

386 To confirm that the variations in R_{des} , and thus in $K_{d,des}$, were due to the same mechanisms
387 affecting sorption, the correlation between the $K_{d,des}$ and K_d was examined. In general, the two
388 parameters were correlated ($K_{d,des La} = 1.36 \times K_{d,La} + 510$, $R^2 = 0.96$; $K_{d,des Lu} = 1.10 \times K_{d,Lu} + 970$,
389 $R^2 = 0.90$). The close correlation between the two variables suggested that $K_{d,des}$, and thus sorption
390 reversibility, could accurately be predicted from the sorption data.

391

392 4. Conclusions

393

394 Although the FEBEX and MX80 bentonites were incubated in the presence of Fe(0) for a
395 relatively short period, structural and sorption data indicated that changes in the solid phase
396 occurred. The formation of either amorphous or crystalline iron oxyhydroxides (goethite), could
397 increase K_d in Fe-treated samples in the low lanthanide concentration scenarios, due to the increase
398 in high affinity sites in the resulting samples. In the presence of goethite lanthanides not only sorbed
399 on smectite sites, but also at the Fe oxide phases. For scenarios with higher lanthanide
400 concentration, the positive effect on the increase in the lanthanide sorption was overcome by the
401 smectite degradation induced by the presence of Fe. This pattern was generally more significant in
402 the Ca than in the water medium.

403 Although corrosion of metal canisters and the presence of alkaline Ca-enriched fluids from
404 the leachates of the surrounding concrete barriers would lead to potential degradation of the clay-
405 engineered barrier in a DGR, whose performance could be at risk because a decrease in their
406 retention capacity could be expected. However, in situ formation of Fe oxyhydroxides with a high-
407 sorption capacity should also be assessed for a better prediction of the changes in the retention
408 capacity of the barrier.

409

410 **Acknowledgements**

411 This research was supported by grants from the Ministry of Education and Science of Spain
412 (projects CTM2008-01147/TECNO and CTM2011-27211), Generalitat de Catalunya (AGAUR
413 2009SGR1188), DGICYT and FEDER funds (project CTQ2010-14874) and from EC funded
414 project within the 6th Framework Programme as the HRM Activity under the Contract MRTN-CT-
415 2006-035957. Additionally, the authors would like to thank Dr. A. Padró for his technical help and
416 assistance in the ICP-OES analyses. XRD measurements were carried out at the CITIUS X-Ray
417 laboratory (Universidad de Sevilla), and SEM/EXD analyses were carried out at the Instituto
418 Ciencia de los Materiales de Sevilla (CICIC).

419

420

421 **References**

422

423 Alba, M.D., Becerro, A.I., Castro, M.A., Perdigón, A.C., 2001. Hydrothermal reactivity of Lu-
424 saturated smectites: Part I. A long-range order study. *Am. Mineral.* 86, 115-123.

425 Alba, M.D., Castro, M.A., Chain, P., Orta, M.M., Pazos, M.C., Pavon, E, 2010. Hydrothermal
426 stability of layered silicates in neutral and acidic media: effect on engineered-barrier safety. *Clay*
427 *Clay Mineral.* 58, 501-514

428 Anastácio, A.S., Aouad, A., Sellin, P., Domingos Fabris, J., Bergaya, F., Stucki, J.W., 2008.
429 Characterization of a redox-modified clay mineral with respect to its suitability as a barrier in
430 radioactive waste confinement. *Appl. Clay Sci.* 39, 172-179.

431 Astudillo, J., 2001. El almacenamiento geológico profundo de los residuos radiactivos de alta
432 actividad. Principios básicos y tecnología. ENRESA, Madrid.

433 Bennett, D.G., Gens, R., 2008. Overview of European concepts for high-level waste and spent fuel
434 disposal with special reference waste container corrosion. *J. Nucl. Mater.* 379, 1-8.

435 Bildstein, O., Trotignon, L., Perronnet, M., Jullien, M., 2006. Modelling iron-clay interactions in
436 deep geological disposal conditions. *Phys. Chem. Earth* 31, 618-625.

437 Bonnot-Courtois, C., Jaffrezic-Renault, N., 1982. Étude des échanges entre terres rares et cations
438 interfoliaires de deux argiles. *Clay Miner.* 17, 409-420.

439 Bradbury, M., Baeyens, B., 2005. Modelling the sorption of Mn(II), Co(II), Ni(II), Cd(II), Eu(III),
440 Am(III), Sn(IV), Th(IV), Np(V) and U(VI) on montmorillonites: Linear free energy relationships
441 and estimates of surface binding constants for some selected heavy metals and actinides.
442 *Geochim. Cosmochim. Acta.* 69, 875-892.

443 Buil, B., Gomez, P., Garralon, A., Turrero, M.J., 2007. Rare-earth elements: a tool for
444 understanding the behavior of trivalent actinides in the geosphere. *Mater. Res. Soc. Symp. Proc.*
445 985, 437-442.

446 Carlson, L., Karnland, O., Oversby, V.M., Rance, A.P., Smart, N.R., Snellma, M., Vähänen, M.,
447 Werme, L.O., 2007. Experimental studies of the interactions between anaerobically corroding
448 iron and bentonite. *Phys. Chem. Earth.* 32, 334-345.

449 Chapman, N., 2006. Geological disposal of radioactive waste – concept, status and trends. *J. Iber.*
450 *Geol.* 32, 7-14.

451 Chapman, N., Smellie, J., 1986. Introduction and summary of the workshop: natural analogues to
452 the conditions around a final repository for high-level radioactive waste. *Chem. Geol.* 55, 167-
453 173.

454 Coppin, F., Berger, G., Bauer, A., Castet, S., Loubet, M., 2002. Sorption of lanthanides on smectite
455 and kaolinite. *Chem. Geol.* 182, 57-68.

456 Coppin, F., Castet, S., Berger, G., Loubet, M., 2003. Microscopic reversibility of Sm and Yb
457 sorption onto smectite and kaolinite: experimental evidence. *Geochim. Cosmochim. Acta.* 67,
458 2515-2527.

459 Do, D., 1998. In *Adsorption analysis: equilibria and kinetics*, vol. 2. Imperial College Press-ICP,
460 London.

461 Dong, W., Wang, X., Bian, X., Wang, A., Du, J., Tao, Z., 2001. Comparative study on
462 sorption/desorption of radioeuropium on alumina, bentonite and red earth: effects of pH, ionic
463 strength, fulvic acid, and iron oxides in red earth. *Appl. Rad. Isot.* 54, 603-610.

464 Fernandez, A., Baeyens, B., Bradbury, M., Rivas, P., 2004. Analysis of the porewater chemical
465 composition of a Spanish compacted bentonite used in an engineered barrier. *Phys. Chem. Earth.*
466 29, 105-118.

467 Galunin, E., Alba, M.D., Santos, M.J., Abrão, T., Vidal, M., 2010. Lanthanide sorption on smectitic
468 clays in presence of cement leachates. *Geochim. Cosmochim. Acta.* 74, 862-875.

469 Galunin, E., Alba, M.D., Santos, M.J., Abrão, T., Vidal, M., 2011. Examination of competitive
470 lanthanide sorption onto smectites and its significance in the management of radioactive waste. *J.*
471 *Hazard. Mater.* 186, 1930-1941.

472 Gaudin, A., Gaboreau, S., Tinseau, E., Bartier, D., Petit, S., Grauby, O., Foct, F., Beaufort, D.,
473 2009. Mineralogical reactions in the Tournemire argillite after in-situ interaction with steels.
474 *Appl. Clay Sci.* 43, 196-207.

475 Grim, R.E., 1968. *Clay Mineralogy*. McGraw-Hill Book Company, New York.

476 Kumpulainen, S., Carlson, T., Muurinen, A., Svensson, D., Sasamoto, H., Yui, M., Wersin, P.,
477 Snellman, M., 2010. Long-term (8-10 y) alteration of bentonite in the presence of metallic iron.
478 Abstracts of the 4th International Meeting “Clays in Natural and Engineered Barriers for
479 Radioactive waste Confinement”, Nantes, France, March 29 – April 1, 97-98.

480 Landais, P., 2006. Advances in geochemical research for the underground disposal of high-level,
481 long-lived radioactive waste in a clay formation. *J. Geochem. Explor.* 88, 32-36.

482 Lantenois, S., 2003. Réactivité fer métal/smectites en milieu hydraté à 80°C. PhD thesis, Université
483 d'Orléans, Orléans, France, 188 pp.

484 Lantenois, S., Lanson, B., Muller, F., Bauer, A., Jullien, M., Plançon, A., 2005. Experimental study
485 of smectite interaction with metal Fe at low temperature: 1. Smectite destabilization, *Clays Clay*
486 *Miner.* 53, 597-612.

487 McCombie, C., Pentz, D.L., Kurzeme, M., Miller, I., 2000. Deep geological repositories: a safe and
488 secure solution to disposal of nuclear wastes. In *GeoEng2000 – An international conference on*
489 *geotechnical & geological engineering, 19-24 November 2000*. Melbourne, Australia. Lancaster,
490 Technomic.

491 Metcalfe, R., Walker, C., 2004. Proceedings of the international workshop on bentonite-cement
492 interactions in repository environment. NUMO-TR-04-05, Nuclear Waste Management
493 Organization of Japan (NUMO).

494 Meunier, A., Velde, B., Griffault, L., 1998. The reactivity of bentonites: a review. An application to
495 clay barrier stability for nuclear waste storage. *Clays Clay Miner.* 33, 187-196.

496 Montes, H.G., Fritz, B., Clement, A., Michau, N., 2007. Modelling of geochemical reactions and
497 experimental cation exchange in MX-80 bentonite. *J. Environ. Manage.* 77, 35-46.

498 Oh, S., Kwak, M.Y., Shin, W.S., 2009. Competitive sorption of lead and cadmium onto sediments.
499 Chem. Eng. J. 152, 376–388.

500 Perronnet, M., Villi eras, F., Jullien, M., Razafitianamaharavo, A., Raynal, J., Bonnin, D., 2007.
501 Towards a link between the energetic heterogeneities of the edge faces of smectites and their
502 stability in the context of metallic corrosion. Geochim. Cosmochim. Acta 71, 1463-1479.

503 Pusch, R., 2006. Engineered Barriers. In *Disposal of hazardous waste in underground mines* (eds.
504 V. Popov and R. Pusch). Wessex Institute of Technology, UK, pp. 35-40.

505 Quinn, K.A., Byrne, R.H., Schijf, J., 2006. Sorption of yttrium and rare earth elements by
506 amorphous ferric hydroxide: Influence of solution complexation with carbonate. Geochim.
507 Cosmochim. Acta 70, 4151-4165.

508 Sanders, D., Kaufhold, S., Hassel, A.W., Dohrmann, R., 2010. Smectite Alteration by anaerobic
509 iron corrosion. Abstracts of the 4rd International Meeting “Clays in Natural and Engineered
510 Barriers for Radioactive waste Confinement”, Nantes, France, March 29 – April 1, 95-96.

511 Savage, D., Watson, C., Benbow, S., Wilson, J., 2010. Modelling iron-bentonite interaction. Appl.
512 Clay Sci. 47, 91-98.

513 Smart, N.R., Blackwood, D.J., Werme, L., 2002. Anaerobic corrosion of carbon steel and cast iron
514 in artificial groundwaters: Part 1 – Gas generation. Corrosion 58, 627-637.

515 Srivastava, V.C., Mall, I.D., Mishra, I.M., 2006. Equilibrium modelling of single and binary
516 adsorption of cadmium and nickel onto bagasse fly ash. Chem. Eng. J. 117, 79–91.

517 The Mathworks, Inc. (2010) *User Guide – Matlab 7.10.0 (R2010a)*. Apple Hill Drive, Natick, MA
518 01760-2098, USA.

519 Tripathy, S., Sriharan, A., Schanz, T., 2004. Swelling pressure of compacted bentonites from
520 diffuse double layer theory. Can. J. Geotech. 41, 437-450.

521 Viani, B.E., Torretto, P.C., Matzen, S.L., 1997. Radionuclide transport through engineered barrier
522 system altered products. UCRL-ID-129281, LLNL, USA.

- 523 Wilson, J., Savage, D., Cuadros, J., Shibata, M., Ragnarsdottir, K.V., 2006a. The effect of iron on
524 montmorillonite stability. (I) Background and thermodynamic considerations. *Geochim.*
525 *Cosmochim. Acta* 70, 306-322.
- 526 Wilson, J., Cressey, G., Cressey, B., Cuadros, J., Ragnarsdottir, K.V., Savage, D., Shibata, M.,
527 2006b. The effect of iron on montmorillonite stability. (II) Experimental investigation. *Geochim.*
528 *Cosmochim. Acta* 70, 323-336.
- 529 Yan, Ch., Li, G., Xue, P., Wei, Q., Li, Q., 2010. Competitive effect of Cu(II) and Zn (II) on the
530 biosorption of lead (II) by *Myriophyllum spicatum*. *J. Hazard. Mater.* 179, 721-728.